COMFORT SILVER 15m x 1m x 3mm

Comfort Silver offers an economic solution for insulating laminate floors with an integral aluminum foil vapour check. Comfort Silver is produced from closed cell Polyethylene Foam which is CFC and HCFC free and 100% recyclable. Due to the low thermal resistance of the product it is ideal for use with underfloor heating systems. Minor floor imperfections may be accommodated by using these materials. The product has very effective acoustic qualities.

Excellent impact sound insulation
Vapour barrier and thermal insulation
30kg/m3 Density
Metallised foil faced
Absorbs minor floor imperfections
Ideal for use with under floor heating systems
Non dusting, non toxic and odourless
Suitable for under floor heating
Overlap for joint sealing protection
Lightweight
Easy to lay
CFC and HCFC free



COMFORT SILVER 15m x 1m x 3mm

TECHNICAL SPECIFICATION

Comfort Silver offers an economic solution for insulating laminate floors with an integral aluminum foil vapour check. Comfort Silver is produced from closed cell Polyethylene Foam which is CFC and HCFC free and 100% recyclable. Due to the low thermal resistance of the product it is ideal for use with underfloor heating systems. Minor floor imperfections may be accommodated by using these materials. The product has very effective acoustic qualities.

TESTS	NORMS	VALUE	
Nominal Thickness	BS4051	3mm	
Tolerances	Thickness	+ or - 2%	
	Width and length	+ or - 3%	
Nominal Weight		90 g/m²	
Apparent Density	DIN 53420 - kg/m3		30
Tensile Strength	DIN 53571 - N/mm2	Along	0.41
		Across	0.29
Elongation	DIN 53571 - %	Along	140
		Across	90
Compressive Stress	DIN 53577 - N/mm2	10%	0.03
		20%	0.04
		30%	0.05
		50%	0.15
		70%	0.38
Compression Set	DIN 53572 - % - N/mm2	24hrs	34
	22h / 20 C / 50%	3 days	9
		7 days	8.1
		14 days	6
Lamda Value	DIN 52612 - W/mk 10%		.054
R Value	m2 K/W		0.050
TOG			0.50
Sound Reduction	BSEN ISO 1408		18dB
Water Absorption	DIN 53428 - Vol %	1hr	1.00
		24hrs	1.40
		28 days	<4
Self Estinguished	UL 94 HF	Class 1	